Test Report No. 7191163498-MEC17/D1-YWA dated 09 Jun 2017 (221412106)

Note: This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.



Choose certainty.

Add value.

SUBJECT:

Large scale surface spread of flame test on "Superlon" Insulation material submitted by Superlon Worldwide Sdn Bhd on 26 May 2017.

TESTED FOR:

Superlon Worldwide Sdn Bhd Lot 2567, Jalan Sungai Jati 41200 Klang Selangor Malaysia

DATE OF TEST:

31 May 2017

PURPOSE OF TEST:

To determine the tendency of the surface of a material or a combination of materials to support the spread of flame across its surface and to classify the surface according to the test given in British Standard 476: Part 7: 1997.

The test was conducted at TÜV SÜD PSB's fire test laboratory located at No. 10 Tuas Avenue 10, Singapore 639134.









LA-2007-0380-A LA-2007-0384-G LA-2007-0381-F LA-2007-0385-E LA-2007-0382-B LA-2007-0386-C LA-2007-0383-G LA-2010-0464-D The results reported herein have been performed in accordance with the terms of accreditation under the Singapore Accreditation Council. Inspections/Calibrations/Tests marked "Not SAC-SINGLAS Accredited" in this Report are not included in the SAC-SINGLAS Accreditation Schedule for our inspection body/laboratory.

Test Report No. 7191163498-MEC17/D1-YWA dated 09 Jun 2017 (221412106)



DESCRIPTION OF SPECIMENS:

Nine pieces of specimen, said to be "Superlon" (25mm thick x 60kg/m³) Insulation material comprising of Nitrile Butadiene Rubber (NBR), each of nominal test size of 885mm x 270mm were submitted.

TEST PROCEDURE:

Prior to test, the specimens were prepared and conditioned in accordance with paragraphs 5.3 to 5.6 of the standard and secured to a specimen holder as described in paragraph 6.3.

Six specimens, backed with calcium silicate board, were tested with the <u>skin (smooth)</u> face exposed to the specified thermal radiation from the apparatus described in paragraph 6.1 of the standard. The intensity of the radiated heat incident on the specimen varies with distance from the hotter end, so that when the specified calibration panel is mounted in the place to be occupied by the specimen, the irradiance of the radiometer is as given in Table 1. The test was terminated when the flame front reached the 825mm reference line, or after 10 minutes has elapsed, whichever is the shorter.

Table 1: Irradiance Along Horizontal Reference Line on the Calibration Board

		-		
Distance along reference line from inside edge of specimen holder	Irradiance kW/m ²			
mm	specified	min.	max.	
75	32.5	32.0	33.0	
225	21.0	20.5	21.5	
375	14.5	14.0	15.0	
525	10.0	9.5	10.5	
675	7.0	6.5	7.5	
825	5.0	4.5	5.5	



Test Report No. 7191163498-MEC17/D1-YWA dated 09 Jun 2017 (221412106)



RESULTS OF TEST:

Specimen No.	1	2	3	4	5	6
Spread of flame at first 1½ minutes (mm)	0	0	0	0	0	0
Distance (mm)	Time of spread of flame to indicated distance					
	(minutes • seconds)					
Start of flaming	nil	nil	nil	nil	nil	nil
75	-	-	-	-	-	-
165						
190						
215						
240						
265	- 4			1		
290	/#					
375						
455						
500		<u> </u>				
525		77				
600				N	0.74	
675				100000		
710	/_		an managana	William		
750			E 100/90),			
785				7 1000	(S)	
825						
865			سو سے			
Time of maximum			1000			
spread of flame	-			-		-
(minutes • seconds)	- A					
Distance of maximum	0	0	0	0	0	0
spread of flame (mm)		LUL		Zames and the same		
Comments	Comments					



Test Report No. 7191163498-MEC17/D1-YWA dated 09 Jun 2017 (221412106)



Classification of Surface Spread of Flame

Classification	Spread of flame at 1.5 min.		Final spread of flame		
	Limit (mm)	Limit for one specimen in sample (mm)	Limit (mm)	Limit for one specimen in sample (mm)	
Class 1	165	165 + 25	165	165 + 25	
Class 2	215	215 + 25	455	455 + 45	
Class 3	265	265 + 25	710	710 + 75	
Class 4	Exceeding the limits for class 3				

CONCLUSION:

In accordance with the class definitions specified in the Standard, the test results show that the sample tested has a <u>Class One</u> Surface Spread of Flame.

REMARKS:

The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Ye Wint Aung

Higher Associate Engineer

Ong Klan\Huat

Senior Associate Engineer

Fire Property Mechanical

Test Report No. 7191163498-MEC17/D1-YWA dated 09 Jun 2017 (221412106)



Please note that this Report is issued under the following terms:

- 1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
- 2. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
- 3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
- 4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
- 5. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.

